

PİŞİRİM İÇİN GEREKLİ ISI DEĞERLERİ (Kcal/Kg)

	100 °C	500 °C	1000 °C	1200 °C
Kaolin	16.1	119.4	420.0	488.8
Kil	15.3	118.0	336.1	452.6
Kuvars	15.2	118.0	261.5	322.0
Potasyum Feldspat	12.9	91.7	240.5	309.7
Vitrifiye Bünye	14.8	109.9	380.8	428.4
Şamotlu (FFC) Bünye	14.5	103.3	283.8	387.6